

ALTURA METALIC

A single component Acrylic Emulsion based sparkling effect finish for interior and exterior walls.

PRODUCT FEATURES

DRYING TIME



SURFACE DRY
30 MINUTES
HARD DRY
4 - 5 HOURS

AVAILABLE PACKS

100ml, 200ml, 500ml, 1 L

COLOURS AVAILABLE



5
SHADES AVAILABLE

FINISH

✓ METALLIC

COVERAGE

50-60 sq.ft/ 2 coats / litre

* Coverage varies depends on the method of application and absorption of the substrate and its condition

HOW TO APPLY

SURFACE PREPARATION

- Ensure that the surface is clean and free from dampness, dirt and other contamination
- For areas severely affected by algae and fungi, ensure that the surface is completely cleaned with Bio-wash before initiating the painting process
- Sand the surface using Sandpaper #180 and clean thoroughly. Ensure that no loose particles are sticking to the wall
- Freshly plastered surfaces must be allowed to cure completely. The coating process can be started after a minimum period of 30 days

APPLICATION PROCEDURE

Interior Walls

- Apply 2 coats of Aquafresh / Altura Wall Primer with an interval of 4 - 5 hrs between subsequent coats.
- Undulations in the wall can be leveled by using MRF VILASA wall putty.
- Putty should be used between the first and second coat of Aquafresh / Altura Wall Primer. Sanding of the putty shall be done as per recommendation. Sanding of the first and second coat of Aquafresh / Altura Wall Primer should be done with Sand paper No. 320
- Apply 2 coats of Altura Metallic Emulsion with an interval of 4 to 5 hours between subsequent coats. Sanding should not be done between the coats

Exterior Walls

- Apply 2 coats of Aquafresh / Altura Wall Primer with an interval of 4 - 5 hrs between subsequent coats. Sanding of the first and second coat of Aquafresh / Altura Wall Primer should be done with Sand paper No. 320
- Apply 2 coats of Altura Metallic Emulsion with an interval of 4 to 5 hours between subsequent coats. Sanding should not be done between the coats.

ADDITIONAL INFORMATION

PRODUCT DISCLAIMER

- The information furnished above are true to the best of our knowledge. The properties specified were tested under controlled conditions. The results may vary depending on the test conditions, condition of the substrate and the test method employed. We are not liable for factors that are beyond our knowledge and control

MRF
Vapocure
Paints



PRODUCT BENEFITS

Advantages

- ✦ Sparkling Effect
- ✦ High Durability
- ✦ UV Resistance
- ✦ High opacity

Where to use

Designed for use on cement plastered Interiors and Exterior walls.

TECHNICAL INFO

Thinner Intake	- 25 – 35 %
Specific gravity	- 1.10 ± 0.03
Non Volatile Matter	- 40.00 ± 2
Typical thickness	- 35 – 40microns/coat
VOC	- < 50 g /l
Recommended Thinner	- Potable Water
Method of application	- Brush / Roller / Spray
Sheen @ 60°	- 25-35 units

*For warranty details, visit our website

Continued

PRECAUTIONS

- The substrate to be coated should be free from dampness as it directly relates to premature paint failure
- The product should be applied at temperatures falling between 20°C to 40°C for optimum performance. Humidity above 75 % is also not favourable
- The product should be stored in a dry, cool and well ventilated place and avoid direct sunlight

SHELF LIFE

3 years from the month of manufacturing for an unopened original container.

RESTRICTION OF HAZARDOUS SUBSTANCES

Lead is not involved at any stage of the manufacturing of the product. Lead content in the film does not exceed 90 parts per million

SAFETY FEATURES

- Use proper PPEs (Personal Protective Equipments) while handling the paint material.
- For more details on safety, refer the MSDS of the product