

AquaFresh

PU WALL PRIMER

AquaFresh Primer is a single pack, IPN based primer for interior and exterior walls.

PRODUCT FEATURES

DRYING TIME



TACK FREE
30 minutes
HARD DRY
72 hours

AVAILABLE PACKS

1L, 4L, 10L, 20L

COVERAGE

85 – 95 sq.ft./ coat /ltr*

* Coverage varies depends on the method of application and absorption of the substrate and its condition

HOW TO APPLY

SURFACE PREPARATION

- Ensure that the surface is clean and free from dampness , dirt and other contamination
- For areas severally affected by algae and fungi ,ensure that the surface is completely cleaned before initiating the painting process
- Sand the surface using Emery Paper No. 180 and clean thoroughly. Ensure that no loose particles are sticking to the wall
- Freshly plastered surfaces must be allowed to cure completely. The coating process can be started after a minimum period of 30 days

APPLICATION PROCESS

Exterior Walls

- Apply 1 - 2 coats of AquaFresh Primer with an interval of 3 - 4 hrs between subsequent coats
- Scuffing of the second coat of AquaFresh Primer with Emery No. 320
- Apply 2 coats of AquaFresh White/shades with an interval of 4 to 5 hours between subsequent coats. Scuffing of the second coat can be done with Emery No. 600

Interior Walls

- Apply 2 coats of AquaFresh Primer with an interval of 3 - 4 hrs between subsequent coats
- Undulations in the wall can be levelled using MRF Vilasa wall putty.
- Putty should be used between the first and second coat of AquaFresh Primer and scuffing of the putty shall be done as per recommendation
- Apply 2 coats AquaFresh White/shades with an interval of 4 to 5 hours between subsequent coats , after subjecting the second coat of Eaze Primer to scuffing using Emery No.320

ADDITIONAL INFORMATION

PRECAUTIONS

The substrate to be coated should be free from dampness as it directly relates to premature paint failure The product should be applied at temperatures falling between 20°C to 40°C for optimum performance. Humidity above 75 % is also not favourable The product should be stored in a dry, cool and well ventilated place.

MRF
Vapocure
Paints



PRODUCT BENEFITS

Advantages

- High opacity
- Good coverage
- Enhances quality of top coats

Where to use

Designed for use on cement plastered interiors and exterior walls.

TECHNICAL INFO

Thinner Intake	- 35 – 45 %
Specific gravity	- 1.46 ± 0.03
Non Volatile Matter	- 56.00 ± 2
Typical thickness	- 40 – 45microns/coat
VOC	- < 50 g /l
Recommended Thinner	- Potable Water
Method of application	- Brush / Roller

PRODUCT DISCLAIMER

The information furnished above are true to the best of our knowledge. The properties specified were tested under controlled conditions. The results may vary depending on the test conditions, condition of the substrate and the test method employed. We are not liable for factors that are beyond our knowledge and control.

RESTRICTION OF HAZARDOUS SUBSTANCES

Lead is not involved at any stage of the manufacturing of the product. Lead content in the film does not exceed 90 parts per million

SHELF LIFE

3 Years from the month of manufacturing for an unopened original container.