

WALL PRIMER

SOLVENT THINNABLE

single pack solvent based primer for Interior Walls

PRODUCT FEATURES

DRYING TIME



Touch free 15 minutes
Tack free 1-2 hours
Hard Dry 5-6 hours

AVAILABLE PACKS

1L, 4L, 20L

COVERAGE

100-120 sq.ft. / litre / coat

* Coverage varies depends on the method of application and absorption of the substrate and its condition

HOW TO APPLY

SURFACE PREPRATION

- Ensure that the surface is clean and free from dampness, dirt and other contamination for areas severally affected by algae and fungi ensure that the surface is completely cleaned before initiating the painting process.
- Freshly plastered surfaces must be allowed to cure completely. The coating process can be started after a minimum period of 30 days
- Sand the surface using Emery Paper No. 180 and clean thoroughly. Ensure that no loose particles are sticking to the wall.

APPLICATION PROCESS

- Apply first coat of Solvent Thinnable wall Primer and allow drying for 6-8 hours
- Smoothen the surface by filling dents with a thin coat of MRF Vilasa Wall Putty and allow drying for 4-6 hours. Sand the surface with emery paper No.220 and wipe clean.
- Apply second coat of Solvent Thinnable wall Primer and allowing drying for 6-8 hours. Sand the surface with emery paper No.320 and wipe clean.
- Apply 2 coats of any MRF Interior Emulsion and Keep an interval of 4- 6 hours in between two coats.

ADDITIONAL INFORMATION

PRODUCT DISCLAIMER

The information furnished above is true to the best of our knowledge. The properties specified were tested under controlled conditions. The results may vary depending on the test conditions, condition of the substrate and the test method employed. We are not liable for factors that are beyond our Knowledge and control.

PRECAUTIONS

- The substrate to be coated should be free from dampness as it directly relates to premature paint failure.
- The product should be applied at temperatures falling between 20°C to 40°C for optimum performance. Humidity above 75 % is also not favourable.
- The product should be stored in a dry, cool and well ventilated place.

SHELF LIFE

One year from the month of manufacturing for an unopened original container.

RESTRICTION OF HAZARDOUS SUBSTANCES

Lead is not involved at any stage of the manufacturing of the product. Lead content in the film does not exceed 90 parts per million



PRODUCT BENEFITS

Advantages



High Coverage



Super smooth Walls

Where to use

Suitable for Interior plastered wall, brick work, concrete and asbestos.

TECHNICAL INFO

Thinner Intake	- 15 – 20 %
Specific gravity	- 1.27 ± 0.03
Non Volatile Matter	- 61 ± 2
Typical thickness	- 40 – 45microns/coat
VOC	- < 50 g /l
Recommended Thinner	- Thinner 555/MTO
Method of application	- Brush / Roller